

# Product Data Sheet

## BENTONITE PELLETS



### 1. APPLICATION

Sealing agent by losses in borehole

### 2. APPEARANCE

Grey Pellets

### 3. TYPICAL PROPERTIES

Specific Gravity	2,2 – 2,5 g/ml
Bulk Density	1,05 – 1,10 g/ml
Free Swelling Volume	> 500 % (after 48 hrs)
Contained Swelling Volume	> 70 % (after 48 hrs)

### 4. PACKAGING

25 kg sacks (40 sacks / 1000 kg)